


New Asphalt Technologies

**26th Annual Region Local
Road Conference**

**Thursday, October 27, 2011
Rapid City, SD**

Ken Swedeen, Dakota Asphalt Pavement Assoc.









Dakota Asphalt Pavement Association Inc.

- Represent over 80 Contractor, Producer, Refiner, Engineering Firms and other Companies involved in the HMA Industry in North and South Dakota
- Dedicated to Quality Asphalt Construction through Education, Research & Training
- Bituminous Certification Courses – NDDOT/SDDOT
- Working with Agencies, LTAP's
- Short Courses – Hot Mix Asphalt Technology
- Research – SDSU, UND, NDSU, SDSM&T

*Let's change the title to
how we can use existing
and new technology to
make our pavements
BETTER!*

Recent HMA Developments

Performance Grades																																														
Avg 7-day Max, °C		PG 44				PG 52				PG 58				PG 64				PG 70				PG 76				PG 82																				
1-day Min, °C		44	46	48	50	52	54	56	58	60	62	64	66	68	70	72	74	76	78	80	82	84	86	88	90	92	94																			
ORIGINAL																																														
	≥ 230 °C	(Flash Point) FP																																												
	≤ 3 Pas @ 135 °C	(Rotational Viscosity) RV																																												
	≥ 1.00 kPa	(Dynamic Shear Rheometer) DSR G*min																																												
		46	52	58	64	70	76	82																																						
(ROLLING THIN FILM OVEN) RTFO Mass Loss ≤ 1.00 %																																														
	≥ 2.20 kPa	46	52	58	64	70	76	82																																						
(PRESSURE AGING VESSEL) PAV																																														
20 Hours, 2.07 MPa		90	96	100	106	110 (116)	116 (122)	122 (128)																																						
	≤ 5000 kPa	(Dynamic Shear Rheometer) DSR G*min																																												
		46	52	58	64	70	76	82	88	94	100	106	112	118	124	130	136																													
(BENDING BEAM RHEOMETER) BBR "S" Stiffness & "m" value																																														
		2	4	6	8	10	12	14	16	18	20	22	24	26	28	30	32																													
Report Value																																														
	≥ 1.00 %	(Bending Beam Rheometer) BBR Physical Hardening																																												
		(Direct Tension) DT																																												
		2	4	6	8	10	12	14	16	18	20	22	24	26	28	30	32																													

October 30, 2003

T3S - Superpave for Low Volume Roads - R. Horan

56

October 30, 2003

T3S - Superpave for Low Volume Roads - R. Horan


56

Performance
Graded Binder
(Modified Binder)

Warm Mix Asphalt




Recent HMA Developments (Con't)



Porous Asphalt Pavement



Recent HMA Developments (Con't)



Thermal & Compaction Control

SMA (Stone Matrix Asphalt)
& Wearing Course
Alternatives



Performance Graded Binder

Superpave performance grading (PG) is based on the idea that an HMA asphalt binder's properties should be related to the conditions under which it is used. For asphalt binders, this involves expected climatic conditions as well as aging considerations.

This may require modifiers be added to the asphalt cement or binder

- Developed out of SHRP in 1990's
- Addressed the weakness of prior Specifications (e.g. Penetration, Viscosity, etc.)
- Modeled on the Engineering Properties of the Binder (and Mixture) at binder storage conditions, plant conditions, aged pavement conditions and pavement service conditions (high pavement temperature ~ summer, cold pavement temperature ~ winter)

- Viscosity
 - viscous effects only
- Penetration
 - empirical measure of viscous and elastic effects
- No Low Temperature Properties Measured
- Problems with Modified Asphalt Characterization
- Specification Proliferation
- Long Term Aging not Considered

Superpave Asphalt Binder Specification


- Grading System Based on Climate

PG 58-28

**Performance
Grade**

**Average 7-day
max pavement
design temp**

**Min pavement
design temp**



Is a PG a Modified Binder ?

Effect of Loading Rate

Reliability

“Rule of 90”



PG 64 - 34 > 64 - - 34 = 98

Probably modified !!


(Depends on Asphalt Source!)

Rounding

Effect of Traffic

PG Binder/Crude Impact

		High Temperature, °C				
		52	58	64	70	76
Low Temperature, °C	-16	52-16	58-16	64-16	70-16	76-16
	-22	52-22	58-22	64-22	70-22	76-22
	-28	52-28	58-28	64-28	70-28	76-28
	-34	52-34	58-34	64-34	70-34	76-34
	-40	52-40	58-40	64-40	70-40	76-40



= Crude Oil




= High Quality Crude Oil



= Modifier Required

- Select Binder (PG) Based on Climate (Location)
- Select Binder (PG) Based on Mix Type, Utilization of RAP and Pavement Design
- Account for Risk Tolerance (e.g. Functional Classification)
- Account for Economics (LCCA)
- Account for Loading/Rate of Loading



Three Closest Weather Stations For Latitude/Longitude= 44.16183/96.75146

General	A=18 km	B=19 km	C=25 km
State	SD	SD	SD
Station ID	0392984	0391076	0399042
County/District	moody	brookings	lake
Weather Station	flandreau 4 sw	brookings 2 ne	wentworth 2 wnw
Elevation, m	476	500	515
Latitude, Longitude	44.05 , 96.60	44.32 , 96.77	44.02 , 97.00
Last Year Data Available	1996	1996	1996

Air Temperature	Mean (Std, N)	Mean (Std, N)	Mean (Std, N)
Average 7-day High Temp.	32.9 (2.1, 39)	32.9 (2.5, 62)	33.4 (2.1, 35)
Low Temperature	-33.4 (2.7, 37)	-33.0 (3.4, 63)	-32.0 (2.6, 38)
Low Temperature Drop	19.6 (5.1, 36)	17.6 (5.8, 61)	16.7 (5.4, 38)
Degree Days Above 30 C	84 (49, 39)	86 (69, 62)	97 (56, 35)

Pavement Temp. and PG	High Low Rel.	High Low Rel.	High Low Rel.
=50% Rel. Pavement Temp.	50.1 -24.6 (50,50)	50.0 -24.4 (50,50)	50.5 -23.6 (50,50)
>50% Rel. PG (High, Low Rel.)	52 -28 (71,88)	52 -28 (70,86)	52 -28 (66,94)
	58 -28 (98,88)	58 -28 (98,86)	58 -28 (98,94)
	58 -34 (98,98)	58 -34 (98,98)	58 -34 (98,98)

Close

PG Chart

Print

Save

Help

Selected Sections

Selected
Not Selected

SD

Weather Station

brookings 2 ne

County

brookings


Latitude

59.83


Longitude

89.19

SD PG Binder Selection (Low Temp-50% Reliability)



SD PG Binder Selection (Low Temp-98% Reliability)




O = -40
O = -34
O = -28


- For new, resurfaced or reconstructed surfaces design the pavement and the asphalt binder
- If a polymer modified binder is called for....“don’t step over dollar bills to pick up pennies”. About \$50/ton of liquid asphalt (\$3/ton of mix) for upgrade 58-28 to 64-28
- A properly designed pavement and binder WILL:
 - Reduce thermal cracking and fatigue cracking saving future maintenance costs for crack sealing, pot hole patching, and associated problems
 - Provide and sustain better ride quality
 - Reduce aging and oxidation
 - Reduce rutting, particularly “green season” rutting (1st or 2nd year summer peak temperatures)

**What is Warm Mix Asphalt
(WMA)???**

Asphalt Binder Properties



WMA Definition



WMA Types

- Asphalt Viscosity-reducing Organic Additives
- Water-bearing Additives
- Water-based Technologies
- Chemical Additives

Review

- WMA is a process of producing bituminous mixture for pavements at a significantly lower temperature than conventional HMA.
- There are more than 20 WMA technologies currently available, at least 15 in the US.
 - Fiber/Organic
 - Chemical
 - Physical
 - Foamed/Foaming Agents
- Goal: Reduce temperature requirements in production from 275-325 deg. F. (HMA) to 200-275 deg. F. (WMA)

Warm Mix Asphalt (WMA)

- Possible Benefits
 - Allowance for Construction Season & Environment
 - More Effective Late Season Paving
 - Portable Plant Setups...Long Hauls
 - Cost Savings: Lower Burner Fuel Usage, Less Waste, Less Equipment Fuel Usage??, More Flexible Project Planning
 - Improve Pavement Quality by Increasing Density Compliance
 - Possible Winter Season Wearing Course?
 - Environmental & Personal Protection
 - Urban Pavement Alternative

Project SD2008-03

Evaluation of Warm Mix Asphalt Concrete Pavement in
South Dakota Conditions

Goals

- Evaluate the suitability of using Warm Mix Asphalt (WMA) in SD
- Assess WMA suitability in all paving applications (e.g. overlays, leveling interim, etc.)
- Evaluate WMA properties (binder, aggregate & mixture)
- Evaluate WMA pavement integrity & durability characteristics w/ HMA
- Emissions evaluation (benefits) of WMA during paving & production

Project Status (Con't)

- Tentative Testing Plan

Mix Type	None	Advera	Evotherm	Foamed
Limestone/PG64-28	X	X	X	X
Quartzite/PG64-28	X		X	X
Nat. Gravel/PG64-28	X		X	X



Without WMA - HMA



With WMA



Warm Mix Asphalt (WMA)

Case Study:
WMA – Nov. 2009; Mission, SD

Warm Mix Asphalt Trial

Turtle Creek Store Mission SD

November 18-20, 2009



Rosebud Sioux Tribe Turtle Creek Shopping Center Mission, SD

Morris Inc.

Pierre, SD

Chris Boom
Asphalt Supt
Morris, Inc.
Pierre, SD

Dan Johnston
Research Asst.
SDDOT
Pierre, SD

Acknowledgement:
SDDOT Materials
Jim Costello &
Rick Rowen

Project Specifics

Transportation of Asphalt: 5 Belly Dump, 40 ton trucks and 2 Side Dump, 40 ton trucks, 3 End Dump 15 ton Trucks. All trucks were tarped.

Transportation Method: Asphalt was hauled 101 miles to Mission, SD, dumped from the 40 ton trucks on an existing pad and reloaded into the end dump trucks via front end loader and skidsteer.

Laydown Equipment: Caterpillar AP1055 Track Paver, CB534 Asphalt Roller

Paving Layout: Varying widths, multiple passes with radius's, under traffic, utilizing flaggers.

Weather: November 18 – Mostly sunny, Low 30, High 57

November 19 – Mostly sunny/windy, Low 21, High 52

November 20 – Partly Cloudy, Low 23, High 56

Project Specifics (Con't)

Project: Turtle Creek Crossing Shopping Center Access Road

Owner: Rosebud Sioux Tribe

Project Location: Mission, SD


Plant Location: Pierre, SD (101 miles from Project)

Asphalt Plant: ADM RoadBuilder 220 TPH

Project Dates: November 18th – 20th, 2009

Project Data: 2-2" Lifts or 900 tons of Class E, Type I Asphalt with PG64-28 Binder with Evotherm added at 0.6% placed on three roads. See Plan.

Paving Layout



Field Mix Analysis (SDDOT)

APA – Rutted Wheel Test



ASPHALT PAVEMENT ANALYZER

Rutting Test Data Sheet

Project No. : Warm Mill 00XF
Mix ID No. : 1
Mix Type : Test
Operator : Kruger

Test No. : R1230-0
Test Date: 01/04/10
Data File : R1230_0.pld
Run Status : Complete

Temperature : 5.8 (deg. C)
Wheel Load : (lbs.)
Hose Pressure : (psi)
Run Time : 2:38:53 (hh:mm:ss)

% Air Void			
Manual Average	Net Man Deflection	APA-DAS Average	Percent Change
	0.000	0.000	
		0.882	
		0.830	25.3
		0.995	19.8
		1.136	14.2
		1.310	15.3
		1.487	13.5
		1.584	5.2
		1.687	7.5
		1.748	3.5
		1.831	4.7
		1.831	0.0

% Air Void			
Manual Average	Net Man Deflection	APA-DAS Average	Percent Change
	0.000	0.000	
		0.693	
		0.850	22.5
		0.890	4.7
		0.914	2.8
		0.952	4.1
		1.075	12.8
		1.217	13.2
		1.238	1.7
		1.357	9.7
		1.429	5.3
		1.429	0.0

% Air Void			
Manual Average	Net Man Deflection	APA-DAS Average	Percent Change
	0.000	0.000	
		1.587	
		1.918	20.8
		2.173	13.3
		2.397	10.3
		2.752	14.8
		3.011	9.4
		3.200	6.3
		3.368	5.3
		3.544	5.2
		3.730	5.3
		3.730	0.0

Average Rut Depth (8000 cycles) = 2.33 mm

Field Core Density Tests

Location 1^{**}: Bottom Lift = 90.5%*
Top Lift = 92.1%

Location 2^{***} Bottom Lift = 91.8%
Top Lift = 90.0%

*All density based on comparison to Maximum Theoretical Density (Rice~Gmm)

**Core Locations not randomly selected. Location 1 typical for temperature and laydown conditions

***Core Location #2 selected as most suspect area (open texture apparent, transport truck 4+ hour wait, temperature to paver < 170 deg. F.

Cross Road – 1st Day












130 deg. Mat
Temp >

A close-up photograph of a yellow steamroller's front section as it paves a road. The machine is moving from left to right, leaving a smooth, dark asphalt surface behind it. The front of the machine is yellow with a white rectangular light on the left and a rectangular vent with four vertical slats on the right. Below the yellow body is a large, rounded, olive-green drum. The background shows a dirt shoulder and a small red flag on a white pole.

140 deg. Mat
Temp >



Warm Mix Application 11/18/09

- Mix production temperature-November 18-312°F
- Last covered 40 ton transport first round departed Pierre 9:55 AM
- Unloaded at DOT yard to remix and load into trucks at 1:10 PM
- AC dump pile core at 250-260°F-remix gave 235-240°F
- Temperature at job delivery- 165-185°F


Warm Mix Application 11/18/09 (con't)

- Paving temperature- 145-165°F
- Mat exhibited no more than a 15-20°F temperature difference.
- Air temperature-high 59°F low 20°F
- Wind-south 6-16 mph-warm
- Marks rolled out down to 130°F
- Paving operations normal


Warm Mix Application 11/19/09

- Mix production temperature- 290°F
- Second run-275°F- “officially” warm mix
- Air temperature-high 48.9°F low 19.9°F
- Wind 13.8-20 mph-cold-gusts to 27 mph
- Paving operations mostly normal-surface more open after paving
- Sections will need flush seal next spring

Laydown on West Road



Transport/Laydown Delivery Transfer



SD2008-03
Border States Paving, Inc.
April 2010 - South Dakota Highway 73

- Thermal Imaging Data Collected
- Full Field Testing Protocol
 - Pavement Cores – Per QC/QA (2 per 1000t subplot)
 - Nuclear Density Testing – Density “Tree” (1 per 500t)
 - Full Volumetric Testing
 - Moisture in Mixture
- Burner Fuel Comparison



SD2008-03
Anderson Western, Inc. (Bismarck, ND)
May 2010 - South Dakota Highway 20



Perpetual Pavements

www.AsphaltAlliance.com

Introduction

- Not a new concept
 - Full-Depth
 - Deep Strength
 - Mill & Fill

**Why consider Perpetual
Pavements????**



Because of this.....



And this.....



And this.....



And this.....



And this.....



And this.....



And this.....probably not so much!!!



1.5 - 3" SMA, OGFC or Superpave

4"
to
6"

Zone
Of High
Compression

*High Modulus
Rut Resistant Material
(Varies As Needed)*


Max Tensile Strain

Flexible Fatigue Resistant
Material 3 - 4"

Pavement Foundation


- > Bottom-up Design and Construction
- > Foundation
 - » **Stable Paving Platform**
 - » **Minimize Seasonal Variability and Volume Change in Service**
- > Fatigue Resistant Lower Asphalt Layer
- > Rut Resistant Upper Asphalt Layers

Mechanistic-Based Design



Mechanistic Performance Criteria

Under ESAL




HMA Considerations

- HMA Base Layer
- Intermediate Layer
- Wearing Surface

› Fatigue Resistant Asphalt Base


- › Minimize Tensile Strain with Pavement Thickness
- › Thicker Asphalt Pavement = **Lower Strain**
- › Strain Below Fatigue Limit = **Indefinite Life**





- Rut Resistant Upper Layers
 - **Aggregate Interlock**
 - » *Crushed Particles*
 - » *Stone-on-Stone Contact*
 - **Binder**
 - » *High Temperature PG*
 - » *Polymers*
 - » *Fibers*
 - **Air Voids**
 - » *Avg. 4% to 6% In-Place*
 - **Surface**
 - » *Renewable*
 - » *Tailored for Specific Use*

Temperature



Impact of Temperature Gradient on Asphalt Grade.

Performance of Washington Interstate Flexible Pavements (based on 180 miles)


Statistic	Time Since Original Construction (years)	Thickness of Original AC (mm (in.))	Time from Original Construction to First Resurfacing (years)
Average	31.6	230 (9.2)	12.4
Range	23 to 39	100 to 345	2 to 25

Ohio Study of Flexible Pavements

- Examined Performance on 4 Interstate Routes
 - HMA Pavements - Up to 34 Years without Rehabilitation or Reconstruction
 - “No significant quantity of work . . . for structural repair or to maintain drainage of the flexible pavements.”
 - Only small incremental increases in Present Cost for HMA pavements.

FHWA - Data from Long-Term Pavement Performance Study

- **Data from GPS-6 (FHWA-RD-00-165)**
- **Conclusions**
 - *Most AC Overlays \geq 15 years before Rehab*
 - *Many AC Overlays > 20 years before Significant Distress*
 - Thicker overlays mean less:
 - Fatigue Cracking
 - Transverse Cracking
 - Longitudinal Cracking




TRL Report 250 Nunn, Brown, Weston & Nicholls

Design of Long-Life Flexible
Pavements for Heavy Traffic

<http://www.trl.co.uk>

Overall Summary

- No structural deformation or roadbase fatigue cracking.
- Distresses confined to surface
 - Rutting
 - Cracking
- Roadbase stiffens with age and reduces deflection.





TRL

Perpetual Pavement

- > Structure Lasts 50+ years.
 - » Bottom-Up Design and Construction
 - » Indefinite Fatigue Life
- > Renewable Pavement Surface.
 - » High Rutting Resistance
 - » Tailored for Specific Application
- > Consistent, Smooth and Safe Driving Surface.
- > Environmentally Friendly
- > Avoids Costly Reconstruction.

References



TRB Circular No. 503
On-line at www4.nas.edu

Porous Asphalt Pavement

The Journal for Surface Water Quality Professionals
Stormwater



**Porous Asphalt Pavement
With Recharge Beds:**

20 Years & Still
Working

“Is it possible to have a stormwater best management practice (BMP) that reduces impervious areas, recharges groundwater, improves water quality, eliminates the need for detention basins, and provides a useful purpose besides stormwater management? This seems like a lot to expect from any stormwater measure, but porous asphalt pavement on top of recharge beds has a proven track record.”

Porous Asphalt Pavement

Gap Graded, Fines Starved, High A/C Content HMA

On Infiltration Bed/Drain Rock





Standard Porous Asphalt Mixes

Sieve Size	% Passing
1/2 in.	100
3/8 in.	95
#4	35
#8	15
#16	10
#30	2

Percent bituminous 5.75-6.0% by weight

Infiltration Bed Recharge Trench







Deicing and Freezing Issues

“One of the most common questions relates to concerns about freezing conditions. Freezing has not been an issue, even in very cold climates. We were quite surprised when the owners of early installations first told us that there was less need to snowplow on the porous pavement surfaces. The underlying stone bed tends to absorb and retain heat so that freezing rain and snow melt faster on the porous pavement. The water drains through the pavement and into the bed below with sufficient void space to prevent any heaving or damage, and the formation of "black ice" is rarely observed. The porous surfaces tend to provide better traction for both pedestrians and vehicles than does conventional pavement. Not a single system has suffered freezing problems”

Thermal & Compaction Technology

Temperature Control
Intelligent Compaction


www.AsphaltAlliance.com

Mix Temperature

- Major Factor in Compaction/Density
- Compaction/Density Major Factor in Pavement Durability
- Uniformity & Consistency, as in all paving operations, are equally important in the final operation: Rolling
- Segregation (mechanical) and Longitudinal Joint Failures are two major contributing factors on premature failure or reduction of pavement life

Cost of Compaction


**Relative cost comparison between
asphalt pavement componets**



- Least expensive part of the paving process
- Aggregates and oil are expensive in comparison
- Compaction adds little to the cost of a ton of asphalt

Effect of Compaction

Relative comparison between each component's contribution to extend pavement life



- Compaction is equally important in extending pavement life
- Saves money in maintenance costs
- Understanding compaction is very important

Importance of Compaction

- Improve Mechanical Stability
- Improve Resistance to Permanent Deformation
- Reduce Moisture Penetration
- Improve Fatigue Resistance
- Reduce Low-Temperature Cracking Potential

Factors Affecting Compaction


- Properties of the Materials
- **Environmental Variables**
- Laydown Site Conditions

Mix Temperature



- Major effect on compaction
- Must compact while oil is still fluid enough to allow aggregate movement
- When oil is stiff, aggregates lock

Time Available for Compaction



- Temperature of mat passing under screed affects mat workability
- Work close to paver when mat is cool
- Add rollers when mat is cool
- Use more force if possible

Intelligent Compaction

- Proper in-place density is vital for good performance
- Conventional compaction equipment and procedures have limitations...
- **Intelligent compaction technology goal is to find *“a better way”***



Conventional Limitations

- The Compaction Process...



Limited "On The Fly" Feedback



Over or Under-Compaction
Can Occur



Conventional Limitations

- Provides little or no “on the fly” feedback for roller operator
 - Better if constant feedback is provided during the compaction process
- Over or under-compaction often occurs
 - Better if operator can tell when and if density has been obtained



Intelligent Compaction

Can we make the process...smarter?



Improved Roller Technology

Sophisticated / Clear
Documentation Systems



Advanced Hardware & Software

Intelligent Compaction

97

IC – Goals / Benefits

- **Short Term**

- Improve density... better performance
- Improve efficiency... cost saving\$
- Increase information... better QC/QA

- **Long Term**

- Comprehensive Compaction Control (CCC)
- Estimate pavement moduli?
- Tie to M-E Design Guide (verify design)?
- Performance specifications?

IC TPF / FHWA Definition

GPS-based documentation systems


- Continuous recordation of materials stiffness
- Continuous recordation of corresponding roller location
- Color-coded mapping of stiffness, temperature and number of passes



Ex. Sakai...



Controller Units



Thermo Gauge



Accelerometer




PC Display

Advantages to GPS system

- Continuous recordation
 - density related outputs
 - corresponding roller location
- Color-coded mapping
- Project mapping
- Easy identification of poor density



Caterpillar




Intelligent Compaction

102


Courtesy of Caterpillar

Sakai IC Roller Project

- Temperature



Accelerated Implementation of IC



Common Methods of Measuring Thermal Segregation

- *Infrared Thermometers – less than \$200*
- *Infrared Cameras – less than \$5K*
- *Pave-IR System – less than \$30K*








Comparison of Thermal Profiling Techniques

Test Device	Strengths	Weaknesses
Handheld IR Thermometer	Inexpensive. Simple to use. Tests independent of paving train.	Requires constant operator attendance. May miss localized defects. No permanent record.
IR Camera	Inexpensive. Simple to use. Tests independent of paving train. More coverage than thermometer.	Requires constant operator attendance. May miss localized defects. No permanent record (usually).
Pave-IR	Does not require constant operator attendance. Provides real-time feedback. Tests virtually full-coverage. Automated data reduction. Permanent record.	Most costly device. Testing coverage could impact risk of finding defects. May include artificial cold spots in data set.

Example report from project with minimal thermal segregation



Tex-244-F Part II


Thermal Profile Summary Report

Profile ID:	Demo - minimal thermal segregation	Profile Date:	9/10/2009 5:13:42 PM
Profile Number:	1	Letting Date:	
Status:	Demonstration	Controlling CSJ:	
County:		Spec Year:	
Tested By:	SDS	Spec Item:	
Test Location:	1019	Special Provision:	
Material Code:	TY C HMA	Mix Type:	
Material Name:			
Producer:			
Area Engineer:		Project Manager:	

Course/Lift:	1	Temperature Differential Threshold:	25.0
Segment Length (ft):	150	Sensors Ignored:	-

Thermal Profile Results Summary				
Number of Profiles	Moderate 25.0°F < differential <= 50.0°F		Severe differential > 50.0°F	
	Number	Percent	Number	Percent
46	8	17	0	0

Example report from project with severe thermal segregation



Tex-244-F Part II

Thermal Profile Summary Report

Profile ID:	Demo - severe thermal segregation	Profile Date:	6/16/2010 5:07:33 AM
Profile Number:	1	Letting Date:	
Status:	severe	Controlling CSJ:	
County:	Demonstration	Spec Year:	
Tested By:	SDS	Spec Item:	
Test Location:	eb	Special Provision:	
Material Code:	SP 12.5	Mix Type:	
Material Name:	Superpave 12.5 PG 64-22		
Producer:			
Area Engineer:		Project Manager:	

Course/Lift:	1	Temperature Differential Threshold:	25.0
Segment Length (ft):	150	Sensors Ignored:	-

Thermal Profile Results Summary				
Number of Profiles	Moderate 25.0°F < differential <= 50.0°F		Severe differential > 50.0°F	
	Number	Percent	Number	Percent
9	0	0	0	100

Conclusions

- *Physical & thermal segregation are the “Cancer of HMA Paving Industry”*
- *You cannot always see it. It grows with time. It often results in the early death of the pavement - often the only reason some HMA pavement are in need of rehabilitation*
- *There are many known & suspected causes & cures – No consensus*
- *Identifying & Eliminating Thermal Segregation is a Major Goal for Quality Paving*

Wearing Course Alternatives

- Chip Seal
- Slurry Seal
- Microsurfacing
- Dense Graded Hot Mix Asphalt
- “Engineered” Wearing Course


SMA (Stone Matrix Asphalt) & Smaller Aggregate Size (NMAAS) Durable Wearing Courses



OFFICE OF MATERIALS & SURFACING

SMA Mix Design

0.45 POWER GRADATION (12.5 mm)



Rut Resistant Wearing Course?



I-29 Sioux Falls South SMA







Review of HMA Research Projects at UND Funded by NDDOT

Presented to the DAPA
Annual Meeting,
Deadwood, SD
January 8-9, 2009



Presented by
Nabil Suleiman, Ph.D.
Civil Engineering Department
University of North Dakota

Evaluation of North Dakota's 4.75 mm Local Gyratory Mixtures for Thin Overlay Applications

4.75 mm Mix Project

- Objectives

- To evaluate the rutting resistance performance of the 4.75 mm mixes
- To evaluate benefits/impacts of the 4.75 mm mixes as thin overlays or as maintenance appl. for med. to low vol. highways
- To show that the 4.75 mm NMAS mixtures are useful in providing utility for fine aggregate stockpile screenings

Original Scope

- Prepare local Superpave samples (4.75 mm NMAS)
 - Binder:PG 64-28, PG 58-28
 - Aggregate blend (%NF/%CF): ..100/0;80/20;60/40
 - Aggregate gradation:4.75 (#4) NMAS
 - Mix Design Air Voids:4%
 - APA Air Voids:7%
- Perform volumetric analysis
- Conduct rut tests using the APA .. Dry and wet

Gradations

Aggregate	Nat. Fines	Crushed Fines
Sieve Size	% Passing	% Passing
5/8" (16mm)	100.0	100.0
1/2" (12.5mm)	100.0	100.0
3/8" (9.5mm)	100.0	99.0
#4 (4.75mm)	96.2	94.9
#8 (2.36mm)	86.1	71.8
#16 (1.18mm)	71.3	47.1
#30 (0.6mm)	50.7	31.0
#50 (0.3mm)	25.4	18.8
#100 (0.15mm)	8.5	11.9
#200 (0.075mm)	5.5	8.9

4.75 mm Mix Project

- Issues

- Realizing the utility of the 4.75 mm mixes as low-cost rut-resistant thin overlays for med. or LVR
- A cost-effective maintenance treatment alternative
- Providing use for CFs and NFs
- Benefit to roadway agencies, local HMA producers, and local aggregate producers on issues regarding aggregate availability and specification compliance

4.75 mm Mix Project

- **Implementation**

- If research study is successful, thin-lift applications of the 4.75 mm mixes can be implemented as cost-effective overlays for medium and LVR roads.
- The 4.75 mm mixtures can also be implemented as a low-cost maintenance treatment alternative for almost all pavement types

- Thanks!

- www.dakota-asphalt.org
- kswedeen@dakota-asphalt.org
- 605-224-8500 Office; 605-360-0045 Mobile
- DAPA Office

Dakota Asphalt Pavement Association
3030 Airport Road, Suite B
Pierre, SD 57501